

SUN PROTECTION

GALA BLACK-OUT 1032

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			127	2000	2300	R	T	A	R	T	A			
1017	nature white	-	-	✓	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
2413	beach	-	-	✓	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
2054	beige	-	-	✓	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
9196	dust grey	-	-	✓	-	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
9193	silver	-	-	✓	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
2412	golden brown	-	-	✓	-	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
9030	light grey	-	-	✓	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
9190	rock	-	-	✓	-	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
2354	copper	-	-	✓	-	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
2400	linen	-	-	✓	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
9092	black	-	-	✓	-	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
2411	dark brown	-	-	✓	-	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Panel Track
 Colour Range 12
 Composition 100 % PES
 Width 2000 / 2300 mm
 Cutting Process cold
 Processing Direction warp & weft


Weight 320 g/m2
 Thickness 0,45 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



Perlex



suitable for workstations



D black-out



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.