SUN PROTECTION

ANTARES 1000

Number	Colour	Width mm 89	127	2300	3000	Light Properties R	T	A	Solar Properties R	T	A	Light Fastness	Gtot - value	FC - value
1021	white	✓	✓	✓	✓	84%	15%	1%	72%	16%	12%	6-7	0,34	0,47
9037	manhattan	✓	✓	✓	✓	54%	9%	37%	52%	8%	40%	6-7	0,43	0,59
9060	mouse grey	✓	✓	✓	✓	30%	0%	70%	29%	2%	69%	6-7	0,53	0,76
2025	beige	✓	✓	✓	✓	71%	15%	14%	64%	17%	19%	6-7	0,46	0,64
2272	sand	✓	✓	✓	✓	69%	9%	22%	64%	13%	23%	6-7	0,38	0,52
9030	grey	✓	✓	✓	✓	55%	5%	40%	52%	7%	41%	6-7	0,43	0,62
9162	dark grey	✓	✓	✓	-	16%	6%	78%	13%	18%	69%	6-7	0,52	0,72
4125	light green	✓	✓	✓	-	68%	9%	23%	60%	13%	27%	6-7	0,39	0,55
9163	black	✓	✓	✓	-	4%	2%	94%	3%	8%	89%	6-7	0,44	0,52
1088	snow white	✓	✓	✓	-	63%	34%	3%	59%	33%	8%	6-7	0,41	0,58
9124	light grey	✓	✓	✓	-	67%	11%	22%	62%	15%	23%	6-7	0,39	0,54
9000	light grey	✓	✓	✓	-	52%	3%	45%	48%	7%	45%	6-7	0,44	0,62
2273	apricot	✓	✓	✓	-	64%	8%	28%	61%	14%	25%	6-7	0,39	0,54
8151	red	✓	✓	✓	-	23%	8%	69%	19%	12%	69%	6-7	0,43	0,60
9001	dark grey	✓	✓	✓	✓	32%	2%	66%	32%	2%	66%	6-7	0,52	0,72
2103	beige	✓	✓	✓	✓	79%	14%	7%	70%	16%	14%	6-7	0,35	0,49
2071	cream	✓	✓	✓	-	70%	12%	18%	63%	15%	22%	6-7	0,51	0,71
6109	yellow	✓	✓	✓	-	49%	11%	40%	45%	15%	40%	6-7	0,39	0,54
2349	dark beige	✓	✓	✓	-	44%	12%	44%	39%	16%	45%	6-7	0,40	0,56
5049	blue	✓	✓	✓	-	31%	1%	68%	41%	6%	53%	6-7	0,38	0,53
5193	royal blue	✓	✓	✓	-	12%	6%	82%	9%	11%	80%	6-7	0,48	0,59

All printed colours and textures only provide orientation and are not reference pattern.

Usable for	Roller / Vertical / Panel Track	Weight	220 g/m2
Colour Range	21	Thickness	0,30 mm
Composition	100 % PES	Moisture proofed	yes
Width	89 / 127 / 2300 / 3000 mm	PVC free	yes
Cutting Process	cold	OekoTex	yes
Processing Direction	warp & weft		

Flame retardant

DIN 4102, B1
NF P 92-503-507,M1
BS 5867 part 2
NFPA 702- USA

suitable for workstations

B semi-transparent

Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

VANCLEWE GERMANY