

# SUN PROTECTION

## SKY-REFLEX 2081

Number	Colour	2400 mm	Light Properties			Solar Properties			UV-Transmission	Openness factor	Gtot value	Fc value	Darkening performance	Glare control	Night privacy	Visual contact with the outside	Control of solar gains
			R	T	A	R	T	A									
1029	white	✓	67%	21%	12%	63%	23%	14%	-	-	0,37	0,63	0	3	3	1	1
1129	off white	✓	65%	21%	14%	61%	23%	16%	-	-	0,37	0,63	0	3	3	1	1
2437	powder puff	✓	65%	20%	15%	61%	22%	17%	-	-	0,37	0,63	0	3	3	1	1
9305	cement	✓	65%	15%	20%	61%	17%	22%	-	-	0,37	0,63	0	3	3	1	1
2499	beach	✓	67%	19%	14%	63%	21%	16%	-	-	0,37	0,63	0	3	3	1	1
2320	cream	✓	65%	17%	18%	61%	19%	20%	-	-	0,37	0,63	0	3	3	1	1
9181	ice	✓	66%	14%	20%	62%	16%	22%	-	-	0,37	0,63	0	3	3	1	1
6132	sunset	✓	57%	27%	16%	53%	29%	18%	-	-	0,40	0,68	0	3	3	1	1
4215	pastel green	✓	63%	13%	24%	59%	15%	26%	-	-	0,38	0,64	0	3	3	1	1
9340	silver-grey	✓	66%	9%	25%	62%	11%	27%	-	-	0,37	0,63	0	3	3	1	1
2500	ivory	✓	55%	19%	26%	51%	21%	28%	-	-	0,41	0,69	0	3	3	1	1
4216	spring green	✓	61%	7%	32%	57%	9%	34%	-	-	0,38	0,64	0	3	3	1	1
9343	ice-grey	✓	66%	9%	25%	62%	11%	27%	-	-	0,37	0,63	0	3	3	1	1
2501	mushroom	✓	62%	6%	32%	58%	8%	34%	-	-	0,38	0,64	0	3	3	1	1
4214	fanfare	✓	51%	2%	47%	47%	4%	49%	-	-	0,42	0,71	0	3	3	1	1
5246	sky blue	✓	63%	10%	27%	59%	12%	29%	-	-	0,38	0,64	0	3	3	1	1
9251	mid grey	✓	32%	7%	61%	28%	9%	63%	-	-	0,48	0,81	0	3	3	1	1
9341	graphit	✓	57%	1%	42%	53%	3%	44%	-	-	0,40	0,68	0	3	3	1	1
5247	jeans	✓	54%	2%	44%	50%	4%	46%	-	-	0,41	0,69	0	3	3	1	1
2502	cappuccino	✓	60%	4%	36%	56%	6%	38%	-	-	0,39	0,66	0	3	3	1	1
9339	dust grey	✓	56%	2%	42%	52%	4%	44%	-	-	0,40	0,68	0	3	3	1	1
5245	petrol blue	✓	53%	1%	46%	49%	3%	48%	-	-	0,41	0,69	0	3	3	1	1
9337	rock grey	✓	61%	9%	30%	57%	11%	32%	-	-	0,38	0,64	0	3	3	1	1
9342	black	✓	57%	27%	16%	53%	29%	18%	-	-	0,40	0,68	0	3	3	1	1

All printed colours and textures only provide orientation and are not reference pattern.

Usable for  
Colour Range  
Composition  
Width  
Cutting Process


Pleated Blinds  
24  
100 % PES  
2400 mm  
cold

Pleating Format  
Weight  
Thickness  
Damp room usable  
PVC free  
OekoTex

20 mm  
115 g/m<sup>2</sup>  
0,18 mm  
yes  
yes  
yes



PerLex



B semi-transparent



suitable for workstations



REACH-compliant



Standard 100 by Oeko-Tex®

Revision 2

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.