

SUN PROTECTION


VISTA-PRINT COTTAGE 2059 / 2065

Number	Colour	Width mm 2400	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
2065	1048-1037 off white*	✓	51%	42%	7%	50%	42%	8%	5-6	>0,45	>0,80
2065	8181-1037 soft rose*	✓	43%	36%	21%	41%	39%	20%	5-6	>0,45	>0,80
2065	5219-1037 sky blue*	✓	48%	37%	15%	46%	37%	17%	5-6	>0,45	>0,80
2059	8181 soft rose	✓	40%	32%	28%	39%	35%	26%	5-6	>0,45	>0,80
2059	1048 off white	✓	49%	40%	11%	48%	40%	12%	5-6	>0,45	>0,80
2059	5219 sky blue	✓	42%	36%	22%	39%	34%	27%	5-6	>0,45	>0,80
2065	2428-1037 birch*	✓	45%	33%	22%	41%	36%	23%	5-6	>0,45	>0,80
2065	2429-1037 latte*	✓	33%	26%	41%	32%	27%	41%	5-6	>0,45	>0,80
2065	6065-1037 melone*	✓	46%	40%	14%	45%	37%	18%	5-6	>0,45	>0,80
2059	2429 latte	✓	30%	24%	46%	34%	27%	39%	5-6	>0,45	>0,80
2059	2428 birch	✓	43%	35%	22%	41%	37%	22%	5-6	>0,45	>0,80
2059	6065 melone	✓	41%	38%	21%	40%	38%	22%	5-6	>0,45	>0,80
2065	9235-1037 mid grey*	✓	35%	31%	34%	37%	30%	33%	5-6	>0,45	>0,80
2059	9235 mid grey	✓	28%	29%	43%	29%	30%	41%	5-6	>0,45	>0,80
2065	4163-1037 lime*	✓	40%	34%	26%	38%	35%	27%	5-6	>0,45	>0,80
2059	4163 lime	✓	38%	31%	31%	37%	32%	31%	5-6	>0,45	>0,80

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds
 Colour Range 8/8
 Composition 100 % PES
 Width 2400 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 80 g/m² | *90 g/m²
 Thickness 0,15 mm | *0,18 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device g_{tot} in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.