

SUN PROTECTION

SPIRIT 1127

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			127	2300	R	T	A	R	T	A				
1083	white		✓	✓	✓	57%	28%	15%	54%	24%	22%	5-6	0,40	0,68
1123	beach white		✓	✓	✓	55%	27%	18%	53%	27%	19%	5-6	0,40	0,68
2345	cream		✓	✓	✓	53%	26%	21%	49%	24%	27%	5-6	0,41	0,69
9212	light grey		✓	✓	✓	49%	26%	25%	41%	30%	29%	5-6	0,44	0,75
2475	champagne		✓	✓	✓	54%	27%	19%	53%	29%	18%	5-6	0,40	0,68
2346	mushroom		✓	✓	✓	54%	26%	20%	51%	25%	24%	5-6	0,41	0,69
9213	granit		✓	✓	✓	35%	24%	41%	33%	24%	43%	5-6	0,47	0,80
6131	soft lemon		✓	✓	✓	52%	25%	23%	51%	27%	22%	5-6	0,41	0,69
2347	bronze		✓	✓	✓	39%	23%	38%	35%	22%	43%	5-6	0,46	0,78
9161	anthracite		✓	✓	✓	19%	20%	61%	17%	18%	65%	5-6	0,52	0,88
8207	rose		✓	✓	✓	53%	27%	20%	54%	25%	21%	5-6	0,40	0,68
4177	olive		✓	✓	✓	36%	20%	44%	32%	18%	50%	5-6	0,47	0,80
2348	chocolate		✓	✓	✓	22%	21%	57%	20%	20%	60%	5-6	0,51	0,86

All printed colours and textures only provide orientation and are not reference pattern.

Usable for	Roller / Vertical / Pleated / Panel Track
Colour Range	13
Composition	100 % PES
Width	89 / 127 / 2300 mm
Cutting Process	hot
Processing Direction	warp

Weight	150 g/m ²
Thickness	0,30 mm
Moisture proofed	yes
PVC free	yes
Halogen free	yes
OekoTex	yes



R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.