

SUN ○ PROTECTION

VISION 1122

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
1080	white	✓	✓	✓	65%	18%	17%	59%	21%	20%	5-6	>0,45	>0,80
2332	cream	✓	✓	✓	54%	12%	34%	48%	14%	38%	5-6	>0,45	>0,80
9156	stone	✓	✓	✓	32%	8%	60%	26%	10%	64%	5-6	>0,45	>0,80
2333	beige	✓	✓	✓	48%	10%	42%	44%	13%	43%	5-6	>0,45	>0,80
9157	steel	✓	✓	✓	9%	6%	85%	8%	7%	85%	5-6	>0,45	>0,80
2344	chocolate	✓	✓	✓	11%	6%	83%	8%	8%	84%	5-6	>0,45	>0,80
2354	copper	✓	✓	✓	39%	11%	50%	34%	14%	52%	5-6	>0,45	>0,80
5189	navy	✓	✓	✓	9%	5%	86%	6%	7%	87%	5-6	>0,45	>0,80
2343	toffee	✓	✓	✓	16%	8%	76%	13%	10%	77%	5-6	>0,45	>0,80
4152	deep green	✓	✓	✓	28%	9%	63%	24%	13%	63%	5-6	>0,45	>0,80

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction


Roller / Vertical / Pleated / Panel Track
10
100 % PES
89 / 127 / 2300 mm
hot
warp

Weight
Thickness
Moisture proofed
PVC free
Halogen free
OekoTex

220 g/m2
0,50 mm
yes
yes
yes
yes



suitable for
workstations



B semi-
transparent



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.