SUN PROTECTION

LUX-PRINT PAISLEY 2021 / 2003

Number	Colour	Width mm 2300	Light Properties R	Light Properties T	Light Properties A	Solar Properties R	Solar Properties T	Solar Properties A	Light Fastness	Gtot - value	FC - value
2021	Lux-Print Paisley 1090-1037 white	✓	52%	29%	19%	48%	33%	19%	6-7	>0,50	>0,75
2021	Lux-Print Paisley 9181-1037 ice	✓	50%	30%	20%	40%	37%	23%	6-7	>0,50	>0,75
2021	Lux-Print Paisley 9090-1037 grey	✓	41%	34%	25%	37%	37%	26%	6-7	>0,50	>0,75
2003	Life-Reflex 1048 off white	✓	65%	28%	7%	61%	31%	8%	6-7	>0,45	>0,75
2003	Life-Reflex 9181 ice	✓	61%	26%	13%	55%	30%	15%	6-7	>0,45	>0,75
2003	Life-Reflex 9090 grey	✓	56%	20%	24%	47%	25%	28%	6-7	>0,45	>0,75
2021	Lux-Print Paisley 2372-1037 ivory	✓	48%	29%	23%	45%	34%	21%	6-7	>0,50	>0,75
2021	Lux-Print Paisley 2371-1037 mushroom	✓	48%	35%	17%	45%	36%	19%	6-7	>0,50	>0,75
2021	Lux-Print Paisley 9178-1037 steel grey	✓	37%	33%	30%	34%	35%	31%	6-7	>0,50	>0,75
2003	Life-Reflex 2372 ivory	✓	51%	27%	22%	43%	30%	27%	6-7	>0,45	>0,75
2003	Life-Reflex 2371 mushroom	✓	51%	21%	28%	41%	24%	35%	6-7	>0,45	>0,75
2003	Life-Reflex 9178 steel grey	✓	37%	14%	49%	26%	19%	55%	6-7	>0,45	>0,75

All printed colours and textures only provide orientation and are not reference pattern.

Usable for	Pleated Blinds
Colour Range	6
Composition	100 % PES
Width	2300 mm
Cutting Process	hot / cold

Pleating Format	20 mm
Weight	90 g/m² / 95 g/m²
Thickness	0,13 / 0,15 mm
Damp room usable	yes
PVC free	yes
OekoTex	yes

Perlex

B semi-transparent

suitable for workstations

by Gerhard van Clewe GmbH & Co.KG

Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

VAN CLEWE GERMANY