

JUNO BLACK-OUT 1112

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
1069	white	✓	✓	✓	64%	0%	36%	60%	0%	40%	6-7	>0,45	>0,60
2275	sand	✓	✓	✓	61%	0%	39%	56%	0%	44%	6-7	>0,45	>0,60
9154	light grey	✓	✓	✓	61%	0%	39%	57%	0%	43%	6-7	>0,45	>0,60
2276	brown	✓	✓	✓	26%	0%	74%	21%	0%	79%	6-7	>0,45	>0,60
9155	mid grey	✓	✓	✓	39%	0%	61%	36%	0%	64%	6-7	>0,45	>0,60
2294	nut	✓	✓	✓	25%	0%	75%	20%	0%	80%	6-7	>0,45	>0,60
9125	slate	✓	✓	✓	17%	0%	83%	14%	0%	86%	6-7	>0,45	>0,60
2295	chocolate	✓	✓	✓	19%	0%	81%	17%	0%	83%	6-7	>0,45	>0,60
5175	aqua	✓	✓	✓	43%	0%	57%	41%	0%	59%	6-7	>0,45	>0,60
4139	spring green	✓	✓	✓	47%	0%	53%	43%	0%	57%	6-7	>0,45	>0,60


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Panel Track
 Colour Range 10 (coloured back side)
 Composition 100 % PES
 Width 89 / 127 / 2300 mm
 Cutting Process cold
 Processing Direction warp

Weight 320 g/m2
 Thickness 0,55 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



suitable for workstations



D black-out



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.