## SUN O PROTECTION

## **MÉLANGE 2056**

Number	Colour	Width mm 2300	Light Properties R T A			Solar Properties R T A			Light Fastness	Gtot - value	FC - value
1080	white	<b>√</b>	66%	27%	7%	58%	29%	13%	5-6	0,41	0,59
2332	cream	<b>√</b>	51%	26%	23%	50%	18%	32%	5-6	0,44	0,63
	brown		28%	18%	54%	27%	20%	53%	5-6	0,55	0,79
	latte	√	31%	20%	49%	27%	21%	52%	5-6	0,55	0,79
	nutwood	<b>√</b>	12%	14%	74%	9%	11%	80%	5-6	0,63	0,90
	asphale	<b>√</b>	18%	18%	64%	15%	25%	60%	5-6	0,61	0,87
9230	rock the state of		34%	19%	47%	31%	27%	42%	5-6	0,53	0,76
9238		<b>√</b>	8%	5%	87%	7%	7%	86%	5-6	0,64	0,91

Usable for Colour Range Composition Width

Roller / Vertical / Pleated / Panel Track

100 % PES 2300 mm **Cutting Process** 

Pleating Format Weight Thickness

PVC free

OekoTex

220 g/m<sup>2</sup> 0,50 mm Damp room usable yes yes

20 mm





workstations transparent





compliant







by Gerhard van Clewe GmbH & Co.KG

Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fcvalue: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

