

SUN PROTECTION

SINFONIA SPECTRA 2068 + VALENTINO 2071

Number	Colour	Width mm 2400	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1110-1037	white Sinfonia Spectra 2068	✓	56%	39%	5%	56%	41%	3%	6-7	0,42	0,6
9267-1037	almond Sinfonia Spectra 2068	✓	44%	32%	24%	42%	35%	23%	6-7	0,49	0,7
9266-1037	linen grey Sinfonia Spectra 2068	✓	43%	27%	30%	40%	30%	30%	6-7	0,49	0,7
4196-1037	wild lime Sinfonia Spectra 2068	✓	49%	28%	23%	48%	33%	19%	6-7	0,46	0,66
1110-1037	white Sinfonia Valento 2071	✓	59%	38%	3%	57%	38%	5%	6-7	0,42	0,6
9267-1037	almond Sinfonia Valento 2071	✓	45%	35%	20%	43%	33%	24%	6-7	0,48	0,69
9266-1037	linen grey Sinfonia Valento 2071	✓	44%	35%	21%	43%	34%	23%	6-7	0,48	0,69
4196-1037	wild lime Sinfonia Valento 2071	✓	50%	36%	14%	49%	35%	16%	6-7	0,45	0,64


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds
 Colour Range 4 / 4
 Composition 100% PES
 Width 2400 mm
 Cutting Process hot
 Pleating Format 20 mm

Weight 110 g/m²
 Thickness 0,20 mm
 Damp room usable yes
 PVC free yes
 Halogen free yes
 OekoTex yes



Relief-
Printing



A
transparent



by Gerhard van Clewe
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.