

SUN PROTECTION

MERKUR-SILVER 1008

All printed colours and textures only provide orientation and are not reference pattern.

Number	Colour	Width mm 2850	Light Properties			Solar Properties			UV- Transm.	Gtot - value	FC - value	Openn. factor
			R	T	A	R	T	A				
325	white	✓	49%	6%	45%	51%	6%	43%	6%	0,44	0,62	2%
9102	silver	✓	50%	5%	45%	51%	6%	43%	4%	0,43	0,62	2%
9103	stone	✓	50%	4%	46%	51%	5%	44%	3%	0,44	0,62	2%
9114	flint	✓	47%	1%	52%	49%	4%	47%	2%	0,44	0,63	2%
2371	mushroom	✓	49%	3%	48%	50%	4%	46%	3%	0,44	0,63	2%
2362	chocolate	✓	47%	1%	52%	50%	4%	46%	1%	0,44	0,63	2%
9104	black	✓	41%	1%	58%	45%	4%	51%	1%	0,46	0,66	2%


Usable for Roller / Pleated / Panel Track
vertical on request
Colour Range 7
Composition 100 % Trevira CS
Width 2850 mm
Cutting Process cold
Processing Direction warp
Weight 170 g/m²
Thickness 0,45 mm
Moisture proofed yes
Light Fastness 5 - 6



Trevira CS®



suitable for Workstations



B semi-transparent



Fluorocarbon free



SVHC free



PVC free



REACH-compliant



Printable



Energy saving



Bisphenol A free



Conflict Minerals free




Smell free



Standard 100 by Oeko-Tex®



by Gerhard van Clewe GmbH & Co.KG



Aluminium Coating



Flame retardant*

DIN 4102, B1
NF P 92-503, M1

* confirmed by Trevira GmbH.
Further certifications on request.



Halogen free



Formaldehyde free



Lead free

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric
• FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a STeP certified company.