

SUN PROTECTION

SPIRIT 2048

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1083	white	✓	57%	28%	15%	54%	24%	22%	5-6	>0,45	>0,80
9212	light grey	✓	49%	26%	25%	41%	30%	29%	5-6	>0,45	>0,80
9213	granit	✓	35%	24%	41%	33%	24%	43%	5-6	>0,45	>0,80
9161	anthracite	✓	19%	20%	61%	17%	18%	65%	5-6	>0,45	>0,80
4177	olive	✓	36%	20%	44%	32%	18%	50%	5-6	>0,45	>0,80
5214	sky blue	✓	28%	25%	47%	23%	20%	57%	5-6	>0,45	>0,80
2345	cream	✓	53%	26%	21%	49%	24%	27%	5-6	>0,45	>0,80
2346	mushroom	✓	54%	26%	20%	51%	25%	24%	5-6	>0,45	>0,80
2347	bronze	✓	39%	23%	38%	35%	22%	43%	5-6	>0,45	>0,80
2348	chocolate	✓	22%	21%	57%	20%	20%	60%	5-6	>0,45	>0,80


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 10
 Composition 100 % PES
 Width 2300 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 150 g/m²
 Thickness 0,30 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



suitable for
workstations



B semi-
transparent



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.