

# SUN PROTECTION

## SKY-UNI 2080


Number	Colour	2400 mm	Light Properties			Solar Properties			UV-Transmission	Openness factor	Gtot value	FC value	Darkening performance	Glare control	Night privacy	Visual contact with the outside	Control of solar gains
			R	T	A	R	T	A									
1029	white	✓	45%	47%	8%	44%	49%	7%	-	-	0,44	0,75	0	2	3	1	1
9305	cement	✓	44%	42%	14%	43%	44%	13%	-	-	0,44	0,75	0	2	3	1	1
1129	off white	✓	47%	45%	8%	46%	47%	7%	-	-	0,43	0,73	0	2	3	1	1
9340	silver-grey	✓	40%	38%	22%	39%	40%	21%	-	-	0,45	0,76	0	2	3	1	1
2499	beach	✓	46%	45%	9%	45%	47%	8%	-	-	0,43	0,73	0	2	3	1	1
4215	pastel green	✓	40%	41%	19%	39%	43%	18%	-	-	0,45	0,76	0	2	3	1	1
2437	powder puff	✓	45%	44%	11%	44%	46%	10%	-	-	0,43	0,73	0	2	3	1	1
5247	jeans	✓	11%	13%	76%	10%	15%	75%	-	-	0,54	0,92	0	2	3	1	0
2320	cream	✓	43%	43%	14%	42%	45%	13%	-	-	0,44	0,75	0	2	3	1	1
2502	cappuccino	✓	28%	30%	42%	27%	32%	41%	-	-	0,49	0,83	0	2	3	1	1
2501	mushroom	✓	34%	35%	31%	33%	37%	30%	-	-	0,47	0,80	0	2	3	1	1
9337	rock grey	✓	25%	26%	49%	24%	28%	48%	-	-	0,50	0,85	0	2	3	1	0
9341	graphit	✓	15%	17%	68%	14%	19%	67%	-	-	0,53	0,90	0	2	3	1	0
9339	dust grey	✓	13%	18%	69%	12%	20%	68%	-	-	0,53	0,90	0	2	3	1	0

All printed colours and textures only provide orientation and are not reference pattern.

Revision 2

Usable for Pleated Blinds  
 Colour Range 14  
 Composition 100 % PES  
 Width 2400 mm  
 Cutting Process hot  
 Processing Direction warp

Pleating Format 20 mm  
 Weight 100 g/m<sup>2</sup>  
 Thickness 0,15 mm  
 Damp room usable yes  
 PVC free yes  
 OekoTex yes



B semi-transparent



suitable for workstations



REACH-compliant



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.