SUN ⊙ PROTECTION

sustainably finished by van Clewe

Recycled

REACh-compliant

Fluorocarbon free*

Smell free*

Halogen free*

PVC free*

ISO 50001
ISO 9001
ISO 14001
ISO: by Gerhard van Clewe GmbH & Co.KG

* free according to recipe

ENERGIE MANAGEMENT ISO 50001:2018
QUALITÄTS MANAGEMENT ISO 9001:2015
UMWELT MANAGEMENT ISO 14001:2015

ECO FABRICS
sustainably finished by VAN CLEWE GERMANY

RE-JUNO 2078

Number	Colour	Width mm 2300	Light Properties R	Light Properties T	Light Properties A	Solar Properties R	Solar Properties T	Solar Properties A	Light Fastness	Gtot - value	FC - value
2275	sand	✓	61%	16%	23%	56%	19%	25%	5-6	0,39	0,66
2276	brown	✓	42%	18%	40%	37%	21%	42%	5-6	0,45	0,76
2294	nut	✓	44%	17%	39%	38%	20%	42%	5-6	0,45	0,76
2295	chocolate	✓	27%	13%	60%	21%	17%	62%	5-6	0,50	0,85
1069	white	✓	69%	19%	12%	63%	22%	15%	5-6	0,37	0,63
9154	light grey	✓	59%	14%	27%	52%	18%	30%	5-6	0,40	0,68
9155	mid grey	✓	18%	13%	69%	14%	17%	69%	5-6	0,53	0,90
9125	slate	✓	13%	11%	76%	10%	14%	76%	5-6	0,54	0,92

All printed colours and textures only provide orientation and are not reference pattern.

Usable for	Roller / Vertical / Pleated / Panel Track	Pleating Format	20 mm
Colour Range	8	Weight	150 g/m²
Composition	100% PES (80% recycled PES)	Thickness	0,35 mm
Width	2300 mm	Damp room usable	yes
Cutting Process	hot	PVC free	yes
Processing Direction	warp	OekoTex	yes

suitable for Workstations

B semi-transparent

OEKO-TEX® INSPIRING CONFIDENCE STeP
18000043 HOHENSTEIN HTTI
Sustainable Textile & Leather Production.
www.oeko-tex.com/step
by Gerhard van Clewe GmbH & Co.KG

OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100
A10-0296 HOHENSTEIN HTTI
Tested for harmful substances.
www.oeko-tex.com/standard100
Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

VAN CLEWE
GERMANY