

SUN PROTECTION


LIFE-UNI 2029

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1029	white	✓	62%	34%	4%	61%	34%	5%	5-6	0,40	0,57
1048	off white	✓	59%	31%	10%	60%	31%	9%	5-6	0,40	0,57
6065	melone	✓	43%	28%	29%	46%	29%	25%	5-6	0,47	0,67
9181	ice	✓	56%	30%	14%	56%	32%	12%	5-6	0,42	0,6
2372	ivory	✓	46%	28%	26%	46%	29%	25%	5-6	0,47	0,67
6113	vanilla	✓	49%	29%	22%	49%	30%	21%	5-6	0,45	0,64
9245	light grey	✓	40%	20%	40%	40%	21%	39%	5-6	0,49	0,7
2320	cream	✓	49%	31%	20%	49%	32%	19%	5-6	0,45	0,64
3072	citrus	✓	38%	25%	37%	37%	25%	38%	5-6	0,51	0,73
9243	dark silver	✓	29%	14%	57%	29%	15%	56%	5-6	0,54	0,77
2437	powder puff	✓	46%	32%	22%	47%	32%	21%	5-6	0,46	0,66
9248	light silver	✓	36%	20%	44%	38%	21%	41%	5-6	0,50	0,71
9244	flint grey	✓	29%	13%	58%	30%	14%	56%	5-6	0,53	0,76
5226	lavender	✓	36%	18%	46%	36%	19%	45%	5-6	0,51	0,73
9090	grey	✓	47%	18%	35%	46%	18%	36%	5-6	0,46	0,66
9186	dark grey	✓	20%	13%	67%	21%	14%	65%	5-6	0,57	0,81
5201	sky blue	✓	47%	23%	30%	48%	23%	29%	5-6	0,45	0,64
2371	mushroom	✓	46%	26%	28%	47%	28%	25%	5-6	0,46	0,66
9179	graphite	✓	19%	13%	68%	20%	14%	66%	5-6	0,58	0,83
4163	lime	✓	48%	23%	29%	48%	26%	26%	5-6	0,46	0,66
2438	tannin	✓	33%	20%	47%	34%	22%	44%	5-6	0,52	0,74
9180	black	✓	14%	9%	77%	14%	11%	75%	5-6	0,60	0,86
4160	light petrol	✓	43%	18%	39%	45%	21%	34%	5-6	0,47	0,67
2381	marone	✓	25%	18%	57%	27%	18%	55%	5-6	0,55	0,79


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds
 Colour Range 24
 Composition 100% PES
 Width 2300 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 80 g/m²
 Thickness 0,15 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



A transparent



suitable for workstations



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.