

TENDENCE 1109

Number	Colour	Width mm				Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	3000	R	T	A	R	T	A			
1072	snow	✓	✓	✓	✓	47%	38%	15%	42%	42%	16%	6-7	0,49	0,70
1071	vanilla ice	✓	✓	✓	✓	44%	29%	27%	43%	31%	26%	6-7	0,48	0,69
9215	silver lining	-	-	✓	-	45%	29%	26%	48%	32%	20%	6-7	0,46	0,66
9141	silver	✓	✓	✓	✓	38%	34%	28%	36%	35%	29%	6-7	0,51	0,73
2320	cream	✓	✓	✓	✓	46%	31%	23%	43%	32%	25%	6-7	0,48	0,69
2371	mushroom	-	-	✓	-	39%	26%	35%	37%	25%	38%	6-7	0,51	0,73
9217	mid grey	-	-	✓	-	24%	20%	56%	15%	22%	63%	6-7	0,60	0,86
2372	ivory	✓	✓	✓	✓	46%	28%	26%	43%	26%	31%	6-7	0,48	0,69
2370	slime grey	✓	✓	✓	✓	27%	23%	50%	26%	24%	50%	6-7	0,55	0,79
9214	iron grey	-	-	✓	-	16%	16%	68%	21%	18%	61%	6-7	0,58	0,83
9140	griffin	✓	✓	✓	✓	15%	15%	70%	13%	14%	73%	6-7	0,61	0,87
9175	dust grey	-	-	✓	-	17%	19%	64%	15%	20%	65%	6-7	0,60	0,86
2365	coffee	-	-	✓	-	13%	15%	72%	11%	13%	76%	6-7	0,62	0,89
9084	clear black	✓	✓	✓	✓	10%	14%	76%	9%	15%	76%	6-7	0,63	0,90
8143	chilli pepper	-	-	✓	-	16%	14%	70%	14%	14%	72%	6-7	0,61	0,87

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
 Colour Range
 Composition
 Width
 Cutting Process
 Processing Direction


Roller / Vertical / Pleated / Panel Track
 15
 100 % PES
 89 / 127 / 2300 / 3000 mm
 hot
 warp & weft

Weight
 Thickness
 Damp room usable
 PVC free
 Halogen free
 OekoTex

120 g/m²
 0,28 mm
 yes
 yes
 yes
 yes



suitable for
workstations



A
transparent



REACH-
compliant



by Gerhard van Cleve
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.