

SUN PROTECTION

JUNO 2041

Number	Colour	Width mm		Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		2300	3000	R	T	A	R	T	A			
1069	white	✓	✓	69%	19%	12%	63%	22%	15%	5-6	>0,45	>0,80
2274	cream	✓	✓	67%	14%	19%	62%	17%	21%	5-6	>0,45	>0,80
8170	rose	✓	-	42%	10%	48%	23%	15%	62%	5-6	>0,45	>0,80
1096	silvery white	✓	-	69%	19%	12%	63%	22%	15%	5-6	>0,45	>0,80
2275	sand	✓	✓	61%	16%	23%	56%	19%	25%	5-6	>0,45	>0,80
8171	orchid	✓	-	49%	15%	36%	44%	18%	38%	5-6	>0,45	>0,80
9154	light grey	✓	✓	59%	14%	27%	52%	18%	30%	5-6	>0,45	>0,80
2276	brown	✓	✓	42%	18%	40%	37%	21%	42%	5-6	>0,45	>0,80
8172	berry	✓	-	35%	17%	48%	18%	21%	61%	5-6	>0,45	>0,80
9195	silvery mid grey	✓	-	18%	13%	69%	14%	17%	69%	5-6	>0,45	>0,80
2330	honey	✓	-	43%	18%	39%	38%	21%	41%	5-6	>0,45	>0,80
8173	aubergine	✓	-	27%	14%	59%	14%	19%	67%	5-6	>0,45	>0,80
9155	mid grey	✓	✓	18%	13%	69%	14%	17%	69%	5-6	>0,45	>0,80
2294	nut	✓	✓	44%	17%	39%	38%	20%	42%	5-6	>0,45	>0,80
4178	peppermint	✓	-	41%	12%	47%	43%	14%	43%	5-6	>0,45	>0,80
5175	aqua	✓	-	47%	19%	34%	41%	23%	36%	5-6	>0,45	>0,80
2295	chocolate	✓	✓	27%	13%	60%	21%	17%	62%	5-6	>0,45	>0,80
4179	soft lime	✓	-	52%	20%	28%	32%	24%	44%	5-6	>0,45	>0,80
5176	night blue	✓	-	18%	12%	70%	13%	16%	71%	5-6	>0,45	>0,80
4140	petrol	✓	-	19%	16%	65%	13%	20%	67%	5-6	>0,45	>0,80
4139	spring green	✓	✓	45%	16%	39%	41%	19%	40%	5-6	>0,45	>0,80
8134	claret	✓	-	24%	15%	61%	18%	19%	63%	5-6	>0,45	>0,80
9125	slate	✓	✓	13%	11%	76%	10%	14%	76%	5-6	>0,45	>0,80

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 23
 Composition 100 % PES
 Width 2300 / 3000 mm
 Cutting Process hot


Pleating Format 20 mm
 Weight 150 g/m²
 Thickness 0,35 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



Teflon



suitable for workstations



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.