

# SUN PROTECTION

## VISTA 2059 / VISTA-REFLEX 2063

Number	Colour	Width mm 2400	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1029	white	✓	53%	37%	10%	57%	41%	2%	5-6	0,39	0,66
1048	off white	✓	49%	40%	11%	48%	40%	12%	5-6	0,42	0,71
2428	birch	✓	43%	35%	22%	41%	37%	22%	5-6	0,44	0,75
9234	light grey	✓	36%	30%	34%	35%	29%	36%	5-6	0,46	0,78
1107	milk	✓	44%	42%	14%	41%	40%	19%	5-6	0,44	0,75
4188	pale lime	✓	38%	34%	28%	36%	35%	29%	5-6	0,46	0,78
9235	mid grey	✓	28%	29%	43%	29%	30%	41%	5-6	0,48	0,81
9215	silver lining	✓	31%	28%	41%	30%	28%	42%	5-6	0,48	0,81
5219	sky blue	✓	42%	36%	22%	39%	34%	27%	5-6	0,45	0,76
9236	steel grey	✓	14%	12%	74%	15%	14%	71%	5-6	0,52	0,88
2429	latte	✓	30%	24%	46%	34%	27%	39%	5-6	0,46	0,78
8185	soft purple	✓	36%	30%	34%	31%	31%	38%	5-6	0,47	0,80

1029	white	✓	57%	37%	6%	53%	37%	10%	6-7	0,40	0,68
1048	off white	✓	55%	37%	8%	53%	38%	9%	6-7	0,40	0,68
2428	birch	✓	49%	26%	25%	44%	30%	26%	6-7	0,43	0,73
9234	light grey	✓	51%	36%	13%	49%	37%	14%	6-7	0,42	0,71
1107	milk	✓	50%	33%	17%	45%	30%	25%	6-7	0,43	0,73
4188	pale lime	✓	47%	29%	24%	45%	32%	23%	6-7	0,43	0,73
9235	mid grey	✓	47%	21%	32%	43%	23%	34%	6-7	0,43	0,73
9215	silver lining	✓	43%	22%	35%	41%	23%	36%	6-7	0,44	0,75
5219	sky blue	✓	48%	32%	20%	47%	32%	21%	6-7	0,42	0,71
9236	steel grey	✓	36%	9%	55%	34%	12%	54%	6-7	0,46	0,78
2429	latte	✓	49%	20%	31%	48%	23%	29%	6-7	0,42	0,71
8185	soft purple	✓	47%	27%	26%	46%	32%	22%	6-7	0,42	0,71

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds  
 Colour Range 12 / 12  
 Composition 100 % PES  
 Width 2400 mm  
 Cutting Process hot


Pleating Format 20 mm  
 Weight 80 / 90 g/m<sup>2</sup>  
 Thickness 0,15 / 0,17 mm  
 Damp room usable yes  
 PVC free yes  
 OekoTex yes



Perlex



suitable for  
workstations



B semi-  
transparent



by Gerhard  
van Cleve  
GmbH & Co.KG



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.