

SUN PROTECTION

CETUS-SILVER 2038

| Number | Colour | Width mm | | Light Properties | | | Solar Properties | | | Light | UV- | Gtot - | FC - | Openn. |
|--------|-----------|----------|---|------------------|-----|-----|------------------|-----|-----|----------|--------|--------|-------|--------|
| | | 2850 | | R | T | A | R | T | A | Fastness | Trans. | value | value | factor |
| 325 | white | | ✓ | 56% | 10% | 34% | 57% | 10% | 33% | 5-6 | 5% | 0,41 | 0,58 | 8% |
| 9102 | silver | | ✓ | 53% | 10% | 37% | 55% | 10% | 35% | 5-6 | 8% | 0,41 | 0,57 | 8% |
| 9103 | stone | | ✓ | 52% | 8% | 40% | 54% | 10% | 36% | 5-6 | 7% | 0,42 | 0,58 | 8% |
| 9114 | flint | | ✓ | 46% | 7% | 47% | 52% | 11% | 37% | 5-6 | 5% | 0,43 | 0,62 | 8% |
| 2371 | mushroom | | ✓ | 54% | 9% | 37% | 56% | 10% | 34% | 5-6 | 5% | 0,41 | 0,59 | 8% |
| 2362 | chocolate | | ✓ | 47% | 4% | 49% | 50% | 6% | 44% | 5-6 | 5% | 0,44 | 0,63 | 8% |
| 9104 | black | | ✓ | 47% | 5% | 48% | 51% | 8% | 41% | 5-6 | 5% | 0,43 | 0,60 | 8% |

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
Colour Range 7
Composition 100% Trevira CS
Width 2850 mm
Cutting Process cold
Pleating Format 20 mm
Weight 140 g/m²
Thickness 0,35 mm
Damp room usable yes



Flame retardant*

DIN 4102, B1
NF P 92-503-507,M1

* confirmed by Trevira GmbH. Further certifications on request.



Smell free



Conflict Minerals free



Fluorocarbon free



SVHC free



PVC free



Bisphenol A free



Lead free



Formaldehyde free



Halogen free



Trevira CS®



Aluminium Coating



Energy saving



Printable



suitable for workstations



B semi-transparent



REACH-compliant



by Gerhard van Cleve GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation. All substances mentioned in the icons, are not used acc. to our recipe.