

SUN PROTECTION

TENDENCE 2044

Number	Colour	Width mm 2250	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1072	snow*	✓	47%	38%	15%	42%	42%	16%	6-7	>0,55	>0,80
1071	vanilla ice*	✓	44%	29%	27%	43%	31%	26%	6-7	>0,55	>0,80
9215	silver lining	✓	45%	29%	26%	48%	32%	20%	6-7	>0,55	>0,80
9141	silver*	✓	38%	34%	28%	36%	35%	29%	6-7	>0,55	>0,80
2320	cream*	✓	46%	31%	23%	43%	32%	25%	6-7	>0,55	>0,80
9216	flax	✓	31%	36%	33%	34%	38%	28%	6-7	>0,55	>0,80
9217	mid grey	✓	24%	20%	56%	15%	22%	63%	6-7	>0,55	>0,80
2372	ivory*	✓	46%	28%	26%	43%	26%	31%	6-7	>0,55	>0,80
2371	mushroom	✓	39%	26%	35%	37%	25%	38%	6-7	>0,55	>0,80
9214	iron grey	✓	16%	16%	68%	21%	18%	61%	6-7	>0,55	>0,80
2311	ginger	✓	22%	18%	60%	19%	22%	59%	6-7	>0,55	>0,80
4141	citronelle	✓	21%	17%	62%	21%	15%	64%	6-7	>0,55	>0,80
9140	griffin*	✓	15%	15%	70%	13%	14%	73%	6-7	>0,55	>0,80
2312	nutmeg	✓	18%	14%	68%	16%	17%	67%	6-7	>0,55	>0,80
2370	slime grey*	✓	27%	23%	50%	26%	24%	50%	6-7	>0,55	>0,80
5180	aqua	✓	32%	35%	33%	30%	32%	38%	6-7	>0,55	>0,80
2319	cardamom	✓	21%	17%	62%	20%	16%	64%	6-7	>0,55	>0,80
9175	dust grey	✓	17%	19%	64%	15%	20%	65%	6-7	>0,55	>0,80
4142	mosaic blue	✓	16%	16%	68%	15%	17%	68%	6-7	>0,55	>0,80
8143	chili pepper	✓	16%	14%	70%	14%	14%	72%	6-7	>0,55	>0,80
2365	coffee	✓	13%	15%	72%	11%	13%	76%	6-7	>0,55	>0,80
5179	royal blue	✓	11%	14%	75%	11%	15%	74%	6-7	>0,55	>0,80
3059	flame	✓	24%	26%	50%	21%	31%	48%	6-7	>0,55	>0,80
9084	clear black*	✓	10%	14%	76%	9%	15%	76%	6-7	>0,55	>0,80


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 24
 Composition 100 % PES
 Width 2250 mm
 Cutting Process hot

Pleating Format 20 mm | * 32 mm
 Weight 120 g/m²
 Thickness 0,28 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



suitable for
workstations



A
transparent



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.