

# SUN PROTECTION

## STAR-LIGHT 1016

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
1017	white	✓	✓	✓	72%	17%	11%	68%	19%	13%	6-7	0,37	0,42
2169	sand	✓	✓	✓	63%	4%	33%	58%	8%	34%	6-7	0,40	0,55
327	grise	✓	✓	✓	63%	5%	32%	60%	11%	29%	6-7	0,36	0,42
2413	beach	✓	✓	✓	55%	2%	43%	53%	6%	41%	6-7	0,43	0,61
9193	silver	✓	✓	✓	43%	1%	56%	39%	1%	60%	6-7	0,49	0,70
2033	caramel	✓	✓	✓	61%	11%	28%	53%	16%	31%	6-7	0,39	0,49

All printed colours and textures only provide orientation and are not reference pattern.

Usable for  
Colour Range  
Composition  
Width  
Cutting Process  
Processing Direction

Roller / Vertical / Panel Track  
6  
100 % PES  
89 / 127 / 2300 mm  
cold  
warp & weft

Weight  
Thickness  
Moisture proofed  
PVC free  
Halogen free  
OekoTex

220 g/m2  
0,35 mm  
yes  
yes  
yes  
yes



Flame  
retardant


DIN 4102, B1



Perlex



suitable for  
workstations



C  
dim out



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.