











# SUN PROTECTION

## INTERIEUR-OFFICE 2102 LIFE BLACK-OUT 2106

Number	Colour	2200 mm	2300 mm	Light Properties			Solar Properties			UV-Transmission	Openness factor	Gtot value	FC value	Darkening performance	Glare control	Night privacy	Visual contact with the outside	Control of solar gains	 
				R	T	A	R	T	A										
1088	snow white 2102	✓		74%	13%	13%	66%	18%	16%	0%	-	0,36	0,61	0	4	4	0	1	 
1000	white 2102	✓		75%	11%	14%	67%	16%	17%	0%	-	0,35	0,59	0	4	4	0	1	 
2025	beige 2102	✓		74%	11%	15%	66%	16%	18%	0%	-	0,36	0,61	0	4	4	0	1	 
2323	sand 2102	✓		73%	7%	20%	65%	12%	23%	0%	-	0,36	0,61	0	4	4	0	1	 
327	grise 2102	✓		72%	9%	19%	65%	14%	21%	0%	-	0,36	0,61	0	4	4	0	1	 
9135	grey 2102	✓		69%	8%	23%	62%	13%	25%	0%	-	0,37	0,63	0	4	4	0	1	 
9058	anthracite 2102	✓		66%	5%	29%	59%	10%	31%	0%	-	0,38	0,64	0	4	4	0	1	 
9128	clay 2102	✓		72%	2%	26%	62%	5%	33%	0%	-	0,37	0,63	0	4	4	0	1	 
1029	white 2106		✓	52%	0%	48%	49%	0%	51%	-	-	0,41	0,69	4	4	4	0	1	
2372	ivory 2106		✓	52%	0%	48%	49%	0%	51%	-	-	0,41	0,69	4	4	4	0	1	
2371	mushroom 2106		✓	52%	0%	48%	49%	0%	51%	-	-	0,41	0,69	4	4	4	0	1	
9178	steel grey 2106		✓	52%	0%	48%	49%	0%	51%	-	-	0,41	0,69	4	4	4	0	1	

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Colour Range 8 | 4  
 Composition 100 % PES  
 Width 2200 | 2300 mm  
 Cutting Process cold  
 Pleated Blinds 8 | 4  
 100 % PES  
 2200 | 2300 mm  
 cold  
 Pleating Format 15 mm | 20 mm  
 Weight 160 g/m<sup>2</sup> | 280 g/m<sup>2</sup>  
 Thickness 0,20 mm | 0,35 mm  
 Damp room usable yes  
 PVC free yes  
 OekoTex yes



suitable for workstations



REACH-compliant



Standard 100 by Oeko-Tex®

Revision 2

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • FC value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.