

SUN C PROTECTION

CLASSIC 1150

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			127	2000	3000	R	T	A	R	T	A			
1078	white	✓	✓	✓	✓	77%	20%	3%	71%	23%	6%	6-7	0,34	0,58
1041	off white	✓	✓	✓	✓	74%	21%	5%	70%	22%	8%	6-7	0,34	0,58
9165	grey	✓	✓	✓	✓	52%	14%	34%	49%	16%	35%	6-7	0,41	0,69
2103	beige	✓	✓	✓	✓	64%	19%	17%	60%	17%	23%	6-7	0,38	0,64
9202	feather gray	✓	✓	✓	✓	42%	14%	44%	40%	12%	48%	6-7	0,44	0,75
9199	flint grey	✓	✓	✓	✓	19%	9%	72%	17%	11%	72%	6-7	0,51	0,86
1098	antique white	✓	✓	✓	✓	69%	19%	12%	66%	20%	14%	6-7	0,36	0,61
9200	silver lining	✓	✓	✓	✓	51%	14%	35%	48%	17%	35%	6-7	0,41	0,69
9198	steel grey	✓	✓	✓	✓	8%	5%	87%	7%	7%	86%	6-7	0,55	0,93
2326	bleached sand	✓	✓	✓	✓	59%	28%	13%	56%	24%	20%	6-7	0,39	0,66
2400	linen	✓	✓	✓	✓	26%	16%	58%	24%	18%	58%	6-7	0,49	0,83
9092	black	✓	✓	✓	✓	1%	2%	97%	1%	5%	94%	6-7	0,57	0,97
2173	wool beige	✓	✓	✓	✓	61%	18%	21%	58%	19%	23%	6-7	0,38	0,64
2309	cream	-	-	✓	-	52%	15%	33%	49%	13%	38%	6-7	0,41	0,69
2399	nomad	✓	✓	✓	✓	38%	12%	50%	35%	10%	55%	6-7	0,46	0,78
9201	smoke grey	✓	✓	✓	✓	37%	11%	52%	35%	12%	53%	6-7	0,46	0,78
4172	shadow green	-	-	✓	-	39%	15%	46%	37%	17%	46%	6-7	0,45	0,76
2401	chocolate	-	-	✓	-	12%	7%	81%	9%	8%	83%	6-7	0,54	0,92
2398	cream pink	-	-	✓	-	63%	17%	20%	61%	18%	21%	6-7	0,37	0,63
2397	pearl	-	-	✓	-	54%	19%	27%	51%	17%	32%	6-7	0,41	0,69
4169	ambrosia	-	-	✓	-	59%	18%	23%	57%	17%	26%	6-7	0,39	0,66
4174	morning mist	-	-	✓	-	52%	16%	32%	49%	18%	33%	6-7	0,41	0,69
5208	gletscher	-	-	✓	-	49%	16%	35%	48%	15%	37%	6-7	0,41	0,69
5205	lavender	-	-	✓	-	38%	12%	50%	37%	11%	52%	6-7	0,45	0,76
9058	anthracite	✓	✓	✓	✓	19%	3%	78%	18%	5%	77%	6-7	0,51	0,86
9119	dark grey	✓	✓	✓	✓	9%	8%	83%	8%	9%	83%	6-7	0,54	0,92
5206	hawaiian ocean	-	-	✓	-	29%	14%	57%	27%	15%	58%	6-7	0,48	0,81
5207	imperial blue	-	-	✓	-	22%	11%	67%	19%	13%	68%	6-7	0,51	0,86
5178	marine	-	-	✓	-	7%	6%	87%	6%	7%	87%	6-7	0,55	0,93
8167	jester red	-	-	✓	-	9%	8%	83%	11%	8%	81%	6-7	0,53	0,90

All printed colours and textures only provide orientation and are not reference pattern.


Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller / Vertical / Panel Track
30
100 % PES
89 / 127 / 2000 / 3000 mm
cold
warp & weft

Weight
Thickness
Moisture proofed
PVC free
Halogen free
OekoTex

190 g/m²
0,30 mm
yes
yes
yes
yes


suitable for
Workstations


B semi-
transparent


by Gerhard van Clewe
GmbH & Co.KG


Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.