## SUN O PROTECTION

## **ALASCO-REFLEX 2016**

Number	Colour	Width mm 2300	Light Properties R T A			Solar Properties R T A			Light Fastness	UV Trans- mission	Gtot - value	FC - value
1029	white	<b>√</b>	68%	28%	4%	61%	33%	6%	6-7	6%	0,40	0,57
9210	silver	<b>√</b>	57%	16%	27%	55%	30%	15%	6-7	2%	0,43	0,61
9134	light grey	<b>✓</b>	50%	8%	42%	52%	25%	23%	6-7	2%	0,44	0,62
9178	steel grey	<b>√</b>	63%	25%	12%	58%	33%	9%	6-7	3%	0,41	0,59
9211	iron	<b>✓</b>	47%	3%	50%	51%	22%	27%	6-7	1%	0,44	0,62
1077	milk	<b>√</b>	67%	30%	3%	59%	34%	7%	6-7	3%	0,40	0,58
2320	cream	<b>√</b>	62%	27%	11%	57%	32%	11%	6-7	3%	0,41	0,57
2372	ivory	<b>✓</b>	65%	25%	10%	59%	31%	10%	6-7	2%	0,41	0,59
4750	brown	<b>✓</b>	57%	16%	27%	55%	28%	17%	6-7	2%	0,42	0,61
2383	mocca	<b>*</b>	47%	2%	51%	48%	23%	29%	6-7	1%	0,44	0,63

Usable for Colour Range Composition Width **Cutting Process** Pleating Format

Pleated Blinds 100 % PES 2300 mm cold

20 mm

110 g/m<sup>2</sup> Weight Thickness 0,20 mm Damp room usable yes PVC free yes Halogen free yes OekoTex yes



DIN 4102, B1



Perlex



transparent



suitable for

workstations









by Gerhard van Clewe GmbH & Co.KG

Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fcvalue: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

