

# SUN PROTECTION


## OPAL 2004

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
325	white	✓	45%	39%	16%	42%	43%	15%	6-7	>0,45	>0,70
327	grise	✓	30%	39%	31%	26%	42%	32%	6-7	>0,45	>0,70
9225	mid grey	✓	27%	38%	35%	24%	37%	39%	6-7	>0,45	>0,70
9150	iron	✓	19%	35%	46%	17%	36%	47%	6-7	>0,45	>0,70
5217	turquoise	✓	11%	37%	52%	8%	39%	53%	6-7	>0,45	>0,70
9084	black	✓	4%	30%	66%	4%	36%	60%	6-7	>0,45	>0,70
8179	bordeaux	✓	20%	36%	44%	18%	38%	44%	6-7	>0,45	>0,70
8180	red	✓	15%	42%	43%	12%	43%	45%	6-7	>0,45	>0,70
1037	nature white	✓	47%	47%	6%	49%	44%	7%	6-7	>0,45	>0,70
2000	sand	✓	36%	45%	19%	34%	46%	20%	6-7	>0,45	>0,70
2419	nomad	✓	43%	42%	15%	38%	46%	16%	6-7	>0,45	>0,70
2420	dark linen	✓	31%	43%	26%	28%	44%	28%	6-7	>0,45	>0,70

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track  
 Colour Range 12  
 Composition 100 % PES  
 Width 2300 mm  
 Cutting Process hot

Pleating Format 20 mm  
 Weight 140 g/m<sup>2</sup>  
 Thickness 0,35 mm  
 Damp room usable yes  
 PVC free yes  
 OekoTex yes



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device g<sub>tot</sub> in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.