

SUN PROTECTION

JUPITER-SILVER 1027

| Number | Colour | Width mm | | | Light Properties | | | Solar Properties | | | UV-Transm. | Gtot - value | FC - value | Openn. factor |
|--------|-----------|----------|-----|------|------------------|----|-----|------------------|----|-----|------------|--------------|------------|---------------|
| | | 89 | 127 | 2850 | R | T | A | R | T | A | | | | |
| 325 | white | % | % | % | 59% | 7% | 34% | 61% | 7% | 32% | 7% | 0,38 | 0,54 | 5% |
| 9102 | silver | % | % | % | 52% | 2% | 46% | 55% | 4% | 41% | 2% | 0,42 | 0,60 | 5% |
| 9103 | stone | % | % | % | 56% | 4% | 40% | 58% | 5% | 37% | 3% | 0,41 | 0,58 | 5% |
| 9114 | flint | % | % | % | 53% | 2% | 45% | 56% | 4% | 40% | 3% | 0,41 | 0,59 | 5% |
| 2371 | mushroom | % | % | % | 53% | 4% | 43% | 55% | 5% | 40% | 3% | 0,42 | 0,60 | 5% |
| 2362 | chocolate | % | % | % | 51% | 2% | 47% | 54% | 4% | 42% | 2% | 0,42 | 0,60 | 5% |
| 9104 | black | % | % | % | 48% | 3% | 49% | 52% | 5% | 43% | 3% | 0,43 | 0,62 | 5% |

All printed colours and textures only provide orientation and are not reference pattern.


Usable for Roller / Vertical / Panel Track
 Colour Range 7
 Composition 100 % Trevira CS
 Width 89 / 127 / 2850 mm
 Cutting Process cold
 Processing Direction warp
 Weight 155 g/m²
 Thickness 0,35 mm
 Moisture proofed yes
 Light Fastness 5 - 6



Trevira CS®



suitable for workstations



B semi-transparent



Fluorocarbon free



SVHC free



PVC free



REACH-compliant



Printable



Energy saving



Bisphenol A free



Conflict Minerals free




Smell free



Standard 100 by Oeko-Tex®



by Gerhard van Clewe GmbH & Co.KG



Aluminium Coating



Flame retardant*

DIN 4102, B1
 NF P 92-503, M1
 DIN EN ISO 13501-1
 NFPA 701 - USA

* confirmed by Trevira GmbH. Further certifications on request.



Halogen free



Formaldehyde free



Lead free

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a STeP certified company.