










# SUN PROTECTION

## HYGIENE

Number	Colour	Width mm					Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value											
		89	127	2300	2500	3000	R	T	A	R	T	A														
325AB	white antibacterial	✓	✓	-	✓	✓	47%	52%	1%	43%	51%	6%	5-6	0,49	0,69											
	<b>JUPITER 1110</b>	Usable for Roller / Vertical / Panel Track					Composition 100 % Trevira CS			Cutting Process cold			Processing Direction warp			Weight 150 g/m2			Thickness 0,30 mm			Flame Retardant DIN 4102, B1 / NF P 92-503-507,M1 / DIN EN ISO 13501-1 / BS 5867 part 2 / UNI 8456-UNI 9174, C1 / EN 13772 class 1 / NFPA 702- USA			  Trevira CS® A transparent	
325AB	white antibacterial	✓	✓	✓	-	✓	54%	45%	1%	50%	43%	7%	6-7	0,45	0,64											
	<b>POLARIS 1014</b>	Usable for Roller / Vertical / Panel Track / Pleated					Composition 100 % Trevira CS			Cutting Process hot			Processing Direction warp & weft			Weight 200 g/m2			Thickness 0,35 mm			Flame Retardant DIN 4102, B1 / NF P 92-503-507,M1 / DIN EN ISO 13501-1 / BS 5867 part 2 / UNI 8456-UNI 9174, C1 / EN 13772 class 1 / NFPA 702- USA			  Trevira CS® B semi-transparent	
1088AB	snow white antibacterial	✓	✓	✓	-	-	63%	34%	3%	59%	33%	8%	6-7	0,41	0,58											
	<b>ANTARES 1000</b>	Usable for Roller / Vertical / Panel Track					Composition 100 % PES			Cutting Process cold			Processing Direction warp & weft			Weight 220 g/m2			Thickness 0,30 mm			Flame Retardant DIN 4102, B1 / NF P 92-503-507,M1 / BS 5867 part 2 / NFPA 702- USA			 B semi-transparent	
1000AB	white antibacterial	✓	✓	✓	-	✓	92%	5%	3%	78%	11%	11%	6-7	0,31	0,43											
	<b>OFFICE 1012</b>	Usable for Roller / Vertical / Panel Track					Composition 100 % PES			Cutting Process cold			Processing Direction warp & weft			Weight 320 g/m2			Thickness 0,40 mm			Flame Retardant DIN 4102, B1 / BS 5867 part 2			   Perlex suitable for workstations C dim out	
1000AB	white antibacterial	✓	✓	✓	-	✓	84%	0%	16%	71%	0%	29%	6-7	0,33	0,46											
	<b>ANTARES BLACK-OUT 1001</b>	Usable for Roller / Vertical / Panel Track					Composition 100 % PES			Cutting Process cold			Processing Direction warp & weft			Weight 420 g/m2			Thickness 0,50 mm			Flame Retardant DIN 4102, B1 / NF P 92-503-507,M1 / BS 5867 part 2 / UNI 8456-UNI 9174, C1 / EN 13772 class 1 / NFPA 702- USA			  suitable for workstations D black-out	

All printed colours and textures only provide orientation and are not reference pattern.

Hygiene effect according to DIN EN ISO 20743^:2013-12  
 Moisture proofed yes  
 PVC free yes

HOHENSTEIN  
INSTITUTE



Hygiene

Flame  
retardant

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.