

CLASSIC-REFLEX 1154

Number	Colour	Width mm		Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		2000	2300	R	T	A	R	T	A			
1041	white	✓	✓	70%	23%	7%	58%	26%	16%	6-7	>0,45	>0,70
9202	feather gray	✓	-	49%	11%	40%	40%	16%	44%	6-7	>0,45	>0,70
2399	nomad	✓	-	46%	18%	36%	38%	15%	47%	6-7	>0,45	>0,70
1098	antique white	✓	✓	71%	20%	9%	65%	18%	17%	6-7	>0,45	>0,70
9200	silver lining	✓	-	53%	16%	31%	48%	19%	33%	6-7	>0,45	>0,70
9165	grey	✓	✓	55%	16%	29%	47%	19%	34%	6-7	>0,45	>0,70
2103	beige	✓	✓	73%	21%	6%	65%	19%	16%	6-7	>0,45	>0,70
2400	linen	✓	-	32%	19%	49%	29%	20%	51%	6-7	>0,45	>0,70
9119	grey	✓	✓	28%	12%	60%	26%	10%	64%	6-7	>0,45	>0,70
2326	bleached sand	✓	✓	62%	24%	14%	57%	22%	21%	6-7	>0,45	>0,70
9201	smoke grey	✓	-	43%	11%	46%	36%	13%	51%	6-7	>0,45	>0,70
9198	steel grey	✓	-	31%	8%	61%	19%	7%	74%	6-7	>0,45	>0,70

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
 Colour Range 12
 Composition 100 % PES
 Width 2000 / 2300 mm
 Cutting Process cold
 Processing Direction warp & weft

Weight 230 g/m²
 Thickness 0,30 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



Perlex



suitable for
workstations



B semi-transparent



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.