

SUN PROTECTION

LUX-PRINT FRESCO N. 2019 / 2003

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
2019	Lux-Print Fresco N. 1090-1037 white	✓	43%	28%	29%	40%	31%	29%	6-7	>0,50	>0,75
2019	Lux-Print Fresco N. 9181-1037 ice	✓	42%	25%	33%	41%	28%	31%	6-7	>0,50	>0,75
2019	Lux-Print Fresco N. 9090-1037 grey	✓	39%	32%	29%	37%	36%	27%	6-7	>0,50	>0,75
2003	Life-Reflex 1048 off white	✓	65%	28%	7%	61%	31%	8%	6-7	>0,45	>0,75
2003	Life-Reflex 9181 ice	✓	61%	26%	13%	55%	30%	15%	6-7	>0,45	>0,75
2003	Life-Reflex 9090 grey	✓	56%	20%	24%	47%	25%	28%	6-7	>0,45	>0,75
2019	Lux-Print Fresco N. 2372-1037 ivory	✓	38%	38%	24%	31%	40%	29%	6-7	>0,50	>0,75
2019	Lux-Print Fresco N. 2371-1037 mushroom	✓	42%	34%	24%	38%	39%	23%	6-7	>0,50	>0,75
2019	Lux-Print Fresco N. 9178-1037 steel grey	✓	23%	18%	59%	20%	23%	57%	6-7	>0,50	>0,75
2003	Life-Reflex 2372 ivory	✓	51%	27%	22%	43%	30%	27%	6-7	>0,45	>0,75
2003	Life-Reflex 2371 mushroom	✓	51%	21%	28%	41%	24%	35%	6-7	>0,45	>0,75
2003	Life-Reflex 9178 steel grey	✓	37%	14%	49%	26%	19%	55%	6-7	>0,45	>0,75


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds
 Colour Range 6
 Composition 100 % PES
 Width 2300 mm
 Cutting Process hot / cold

Pleating Format 20 mm
 Weight 90 g/m² / 95 g/m²
 Thickness 0,13 / 0,15 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



Perlex



B semi-transparent



suitable for workstations



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.