

# SUN PROTECTION

## LUNA BLACK-OUT 1005

Number	Colour	Width mm		Light Properties			Solar Properties			Light	Gtot -	FC -
		2000	3000	R	T	A	R	T	A	Fastness	value	value
1039	nature white	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2141	fleece	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9191	light grey	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2490	cream	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2326	bleached sand	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9322	steel	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2323	sand	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2491	hazelnut	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9193	silver	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9197	iron	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2393	cinder	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9192	black	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58

All printed colours and textures only provide orientation and are not reference pattern.

Usable for  
Colour Range 12  
Composition 100 % PES  
Width 2000 / 3000 mm  
Cutting Process cold  
Processing Direction warp & weft

Weight 360 g/m²  
Thickness 0,55 mm  
Moisture proofed yes  
PVC free yes  
Halogen free yes  
OekoTex yes



suitable for  
Workstations



D  
black-out



by Gerhard van Clewe  
GmbH & Co.KG



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.