

SUN PROTECTION

ANTARES-REFLECTION 1061

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
1021	white	✓	✓	✓	87%	12%	1%	80%	13%	7%	6-7	0,30	0,42
9124	light grey	✓	✓	✓	85%	8%	7%	78%	11%	11%	6-7	0,31	0,43
2025	beige	✓	✓	✓	80%	11%	9%	73%	13%	14%	6-7	0,33	0,46
9058	anthracite	✓	✓	✓	78%	3%	19%	71%	6%	23%	6-7	0,34	0,47
9037	manhattan	✓	✓	✓	81%	8%	11%	74%	11%	15%	6-7	0,33	0,45

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range 5
Composition 100 % PES
Width 89 / 127 / 2300 mm
Cutting Process cold
Processing Direction warp & weft

Roller / Vertical / Panel Track
Weight 260 g/m2
Thickness 0,35 mm
Moisture proofed yes
PVC free yes
OekoTex yes




Flame retardant

DIN 4102, B1
BS 5867 part 2



suitable for workstations



C dim out



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.