

SUN PROTECTION

JUPITER 1110

Number	Colour	Width mm			Light Properties			Solar Properties			UV-Transm.	Gtot - value	FC - value	Openn. factor
		89	127	3000	R	T	A	R	T	A				
325	white	✓	✓	✓	47%	52%	1%	43%	51%	6%	12%	0,49	0,69	5%
1070	nature white	✓	✓	✓	53%	44%	3%	49%	44%	7%	11%	0,46	0,66	5%
9102	silver	✓	✓	✓	44%	36%	20%	45%	42%	13%	11%	0,47	0,68	5%
2000	sand	✓	✓	✓	53%	39%	8%	52%	40%	8%	21%	0,44	0,63	5%
9103	stone	✓	✓	✓	29%	21%	50%	41%	33%	26%	14%	0,49	0,70	5%
2363	beige	✓	✓	✓	50%	34%	16%	49%	37%	14%	13%	0,45	0,64	5%
2370	slime grey	✓	✓	✓	23%	13%	64%	39%	28%	33%	9%	0,50	0,71	5%
2371	mushroom	✓	✓	✓	36%	22%	42%	45%	33%	22%	33%	0,47	0,67	5%
9114	flint	✓	✓	✓	15%	12%	73%	33%	31%	36%	8%	0,53	0,75	5%
2260	espresso	✓	✓	✓	13%	9%	78%	31%	29%	40%	6%	0,53	0,76	5%
9104	black	✓	✓	✓	3%	3%	94%	26%	23%	51%	4%	0,55	0,79	5%
2362	chocolate	✓	✓	✓	7%	3%	90%	31%	25%	44%	3%	0,52	0,75	5%

All printed colours and textures only provide orientation and are not reference pattern.


Usable for Roller / Vertical / Panel Track
 Colour Range 12
 Composition 100 % Trevira CS
 Width 89 / 127 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft
 Weight 150 g/m²
 Thickness 0,30 mm
 Moisture proofed yes
 Light Fastness 5 - 6



Trevira CS®



suitable for Workstations



B semi-transparent



Fluorocarbon free



SVHC free



PVC free



REACH-compliant



Printable



Energy saving



Bisphenol A free



Conflict Minerals free



Smell free



Standard 100 by Oeko-Tex®



by Gerhard van Clewe GmbH & Co.KG



Flame retardant*

DIN 4102, B1
 NF P 92-503, M1
 UNI 8456-UNI 9174, C1

* confirmed by Trevira GmbH. Further certifications on request.



Halogen free



Formaldehyde free



Lead free

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric
 • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a STeP certified company.