

JUNO-REFLEX 1132

Number	Colour	Width mm	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			2300	R	T	A	R	T			
1069	white	✓	68%	13%	19%	62%	16%	22%	5-6	>0,45	>0,75
2275	sand	✓	63%	9%	28%	55%	12%	33%	5-6	>0,45	>0,75
4139	spring green	✓	46%	5%	49%	42%	9%	49%	5-6	>0,45	>0,75
9154	light grey	✓	54%	12%	34%	52%	16%	32%	5-6	>0,45	>0,75
2276	brown	✓	38%	11%	51%	36%	14%	50%	5-6	>0,45	>0,75
5175	aqua	✓	29%	10%	61%	25%	15%	60%	5-6	>0,45	>0,75
9155	mid grey	✓	42%	9%	49%	39%	14%	47%	5-6	>0,45	>0,75
2294	nut	✓	23%	8%	69%	19%	13%	68%	5-6	>0,45	>0,75
9125	slate	✓	19%	9%	72%	18%	13%	69%	5-6	>0,45	>0,75
2295	chocolate	✓	33%	7%	60%	27%	11%	62%	5-6	>0,45	>0,75

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Pleated / Panel Track
 Colour Range 10
 Composition 100 % PES
 Width 2300 mm
 Cutting Process cold
 Processing Direction warp

Weight 170 g/m2
 Thickness 0,40 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



Perlex



suitable for workstations



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.