

## MÉLANGE BLACK-OUT 1167

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1080	white	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70
2332	cream	✓	46%	0%	54%	40%	0%	60%	6-7	>0,40	>0,70
2434	nutwood	✓	46%	0%	54%	40%	0%	60%	6-7	>0,40	>0,70
2379	chocolate	✓	13%	0%	87%	12%	0%	88%	6-7	>0,40	>0,70
9230	rock	✓	29%	0%	71%	22%	0%	78%	6-7	>0,40	>0,70
9238	steel	✓	29%	0%	71%	22%	0%	78%	6-7	>0,40	>0,70


All printed colours and textures only, provide orientation and are not reference pattern.

Usable for Roller / Panel Track / Vertical  
 Colour Range 6  
 Composition 100 % PES  
 Width 89 / 127 / 2300 mm  
 Cutting Process cold  
 Processing Direction warp

Weight 420 g/m<sup>2</sup>  
 Thickness 0,60 mm  
 Moisture proofed yes  
 PVC free yes  
 Halogen free yes  
 OekoTex yes



suitable for  
workstations



D  
black-out



Standard 100  
by Oeko-Tex®



by Gerhard van Cleve  
GmbH & Co.KG

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric  
 • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a STeP certified company.