

# SUN PROTECTION

## ANTARES-PERLEX 1002

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
1021	white	✓	✓	✓	85%	9%	6%	76%	12%	12%	6-7	0,32	0,45
2025	beige	✓	✓	✓	79%	10%	11%	71%	13%	16%	6-7	0,34	0,47
2103	beige	✓	✓	✓	84%	9%	7%	76%	12%	12%	6-7	0,32	0,45
9124	light grey	✓	✓	✓	75%	7%	18%	68%	12%	20%	6-7	0,36	0,49
9030	grey	✓	✓	✓	70%	3%	27%	64%	6%	30%	6-7	0,38	0,54
2272	sand	✓	✓	✓	77%	7%	16%	70%	11%	19%	6-7	0,35	0,48
9037	manhattan	✓	✓	✓	75%	3%	22%	67%	6%	27%	6-7	0,36	0,49
9060	mouse grey	✓	✓	✓	59%	0%	41%	52%	1%	47%	6-7	0,43	0,61
2071	cream	✓	✓	✓	77%	8%	15%	65%	10%	25%	6-7	0,34	0,48
9000	light grey	✓	✓	✓	70%	5%	25%	63%	8%	29%	6-7	0,38	0,53
9001	dark grey	✓	✓	✓	58%	1%	41%	51%	1%	48%	6-7	0,43	0,59
2273	apricot	✓	✓	✓	74%	6%	20%	68%	11%	21%	6-7	0,35	0,49
2349	dark beige	✓	✓	✓	56%	4%	40%	43%	9%	48%	6-7	0,43	0,59
4125	light green	✓	✓	✓	76%	7%	17%	69%	11%	20%	6-7	0,35	0,49
5049	blue	✓	✓	✓	61%	1%	38%	59%	4%	37%	6-7	0,39	0,55

All printed colours and textures only provide orientation and are not reference pattern.

Usable for  
Colour Range  
Composition  
Width  
Cutting Process  
Processing Direction

Roller / Vertical / Panel Track  
15  
100 % PES  
89 / 127 / 2300 mm  
cold  
warp & weft

Weight  
Thickness  
Moisture proofed  
PVC free  
OekoTex

240 g/m2  
0,35 mm  
yes  
yes  
yes



Flame  
retardant


DIN 4102, B1  
BS 5867 part 2



Perlex



suitable for  
workstations



C  
dim out



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.