

SUN PROTECTION

ANTARES 1000


Number	Colour	Width mm				Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	3000	R	T	A	R	T	A			
1021	white	✓	✓	✓	✓	84%	15%	1%	72%	16%	12%	6-7	0,34	0,58
2103	beige	✓	✓	✓	✓	79%	14%	7%	70%	16%	14%	6-7	0,34	0,58
9030	grey	✓	✓	✓	✓	55%	5%	40%	52%	7%	41%	6-7	0,40	0,68
9124	light grey	✓	✓	✓	✓	67%	11%	22%	62%	15%	23%	6-7	0,37	0,63
2025	beige	✓	✓	✓	✓	71%	15%	14%	64%	17%	19%	6-7	0,36	0,61
9060	mouse grey	✓	✓	✓	✓	30%	0%	70%	29%	2%	69%	6-7	0,47	0,80
9000	light grey	✓	✓	✓	-	52%	3%	45%	48%	7%	45%	6-7	0,41	0,69
2272	sand	✓	✓	✓	✓	69%	9%	22%	64%	13%	23%	6-7	0,36	0,61
9162	dark grey	✓	✓	✓	✓	16%	6%	78%	13%	18%	69%	6-7	0,53	0,90
9037	manhattan	✓	✓	✓	✓	54%	9%	37%	52%	8%	40%	6-7	0,40	0,68
2445	beach	✓	✓	✓	-	50%	5%	45%	48%	7%	45%	6-7	0,41	0,69
9163	black	✓	✓	✓	-	4%	2%	94%	3%	8%	89%	6-7	0,56	0,95
1088	snow white	✓	✓	✓	-	63%	34%	3%	59%	33%	8%	6-7	0,38	0,64
2071	cream	✓	✓	✓	-	70%	12%	18%	63%	15%	22%	6-7	0,37	0,63
2349	dark beige	✓	✓	✓	✓	44%	12%	44%	39%	16%	45%	6-7	0,44	0,75
4125	light green	✓	✓	✓	-	68%	9%	23%	60%	13%	27%	6-7	0,38	0,64
5049	blue	✓	✓	✓	-	31%	1%	68%	41%	6%	53%	6-7	0,44	0,75
9001	dark grey	✓	✓	✓	✓	32%	2%	66%	32%	2%	66%	6-7	0,46	0,78

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Panel Track
 Colour Range 18
 Composition 100 % PES
 Width 89 / 127 / 2300 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft
 Weight 220 g/m²
 Thickness 0,30 mm
 Moisture proofed yes
 PVC free yes
 OekoTex yes


 DIN 4102, B1
 NF P 92-503-507, M1
 BS 5867 part 2
 NFPA 701- USA
 Flame retardant


 suitable for workstations


 B semi-transparent


 REACH-compliant


 by Gerhard van Clewe GmbH & Co.KG


 Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.