


SUN PROTECTION

CRUSH-REFLEX 2046

Number	Colour	Width mm 2400	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1029	white	✓	61%	37%	2%	57%	37%	6%	6-7	0,40	0,57
2428	birch	✓	49%	26%	25%	44%	30%	26%	6-7	0,45	0,64
5234	cloudy blue	✓	58%	25%	17%	57%	23%	20%	6-7	0,41	0,59
1037	nature white	✓	60%	37%	3%	59%	36%	5%	6-7	0,40	0,57
2457	ivory	✓	53%	32%	15%	49%	31%	20%	6-7	0,43	0,61
5235	blue ice	✓	57%	22%	21%	56%	28%	16%	6-7	0,41	0,59
9288	dust	✓	58%	28%	14%	55%	29%	16%	6-7	0,41	0,59
2454	vanilla	✓	54%	34%	12%	54%	30%	16%	6-7	0,43	0,61
4204	lime cream	✓	56%	25%	19%	53%	27%	20%	6-7	0,42	0,60
9282	silver rock	✓	52%	27%	21%	56%	28%	16%	6-7	0,42	0,60
6128	tender yellow	✓	49%	33%	18%	50%	32%	18%	6-7	0,45	0,64
8204	soft rose	✓	56%	25%	19%	52%	19%	29%	6-7	0,42	0,60
9281	silver grey	✓	47%	28%	25%	50%	29%	21%	6-7	0,46	0,66
2455	beach	✓	48%	33%	19%	47%	33%	20%	6-7	0,46	0,66
8203	lavender	✓	54%	20%	26%	51%	20%	29%	6-7	0,43	0,61
9286	ash grey	✓	53%	19%	28%	54%	20%	26%	6-7	0,43	0,61
6130	soft yellow	✓	55%	23%	22%	56%	22%	22%	6-7	0,42	0,60
4205	fresh mint	✓	55%	15%	30%	55%	16%	29%	6-7	0,42	0,60
9283	steel blue	✓	38%	17%	45%	40%	16%	44%	6-7	0,50	0,71
6129	amber yellow	✓	51%	31%	18%	50%	30%	20%	6-7	0,44	0,63
2456	moon rock	✓	37%	14%	49%	38%	15%	47%	6-7	0,50	0,71
9236	steel grey	✓	36%	9%	55%	34%	12%	54%	6-7	0,50	0,71
4203	apple green	✓	47%	31%	22%	49%	30%	21%	6-7	0,46	0,66
2458	morel	✓	43%	10%	47%	44%	11%	45%	6-7	0,47	0,67

Usable for Pleated Blinds
 Colour Range 24
 Composition 100 % PES
 Width 2400 mm
 Cutting Process hot
 Pleating Format 20 mm

Weight 90 g/m²
 Thickness 0,50 mm
 Damp room usable yes
 PVC free yes
 Halogen free yes
 OekoTex yes



R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.