SUN O PROTECTION

CORONA 2053

Number	Colour	Width mm 2000	Light Properties R T A			Solar Properties R T A			Light Fastness	Gtot - value	FC - value
325	white	√	51%	46%	3%	45%	49%	6%	5-6	0,43	0,73
8177	rose blush	√	26%	23%	51%	24%	18%	58%	6-7	0,49	0,83
4181	lime blush	√	46%	29%	25%	44%	27%	29%	6-7	0,43	0,73
9102		✓	44%	38%	18%	40%	40%	20%	6-7	0,45	0,76
9219	mid grey	✓	39%	32%	29%	37%	29%	34%	6-7	0,45	0,76
1077		√	49%	45%	6%	44%	47%	9%	6-7	0,43	0,73
2416	soft cream	√	38%	25%	37%	41%	25%	34%	6-7	0,44	0,75
2000	sand III II I	✓	48%	42%	10%	43%	45%	12%	6-7	0,44	0,75
2363	beige	✓	46%	40%	14%	42%	42%	16%	6-7	0,44	0,75
2369	toffee	✓	39%	32%	29%	35%	35%	30%	6-7	0,46	0,78

Usable for Colour Range Composition

Roller / Vertical / Pleated / Panel Track

10 100 % PES 2000 mm Width **Cutting Process** hot

Pleating Format 20 mm Weight 140 g/m² Thickness 0,30 mm Damp room usable yes PVC free yes OekoTex yes







B semi-transparent by Gerhard van Clewe fmbH & Co.KG by Oeko-Tex® Standard 100

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

