

SUN PROTECTION

FOCUS-REFLEX 2077

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1029	white	✓	65%	32%	3%	66%	31%	3%	6-7	0,36	0,61
1048	off white	✓	62%	30%	8%	61%	31%	8%	6-7	0,38	0,64
2320	cream	✓	49%	29%	22%	50%	27%	23%	6-7	0,41	0,69
2372	ivory	✓	48%	27%	25%	47%	25%	28%	6-7	0,42	0,71
2438	tannin	✓	35%	19%	46%	32%	20%	48%	6-7	0,47	0,80
2371	mushroom	✓	49%	23%	28%	48%	21%	31%	6-7	0,42	0,71
9181	ice	✓	59%	28%	13%	60%	26%	14%	6-7	0,38	0,64
9244	flint grey	✓	33%	18%	49%	32%	17%	51%	6-7	0,47	0,80
9245	light grey	✓	53%	21%	26%	54%	20%	26%	6-7	0,40	0,68
9186	dark grey	✓	25%	13%	62%	24%	15%	61%	6-7	0,49	0,83
9090	grey	✓	53%	23%	24%	51%	21%	28%	6-7	0,41	0,69
9179	graphite	✓	21%	12%	67%	21%	13%	66%	6-7	0,50	0,85
9178	steel grey	✓	30%	16%	54%	36%	13%	51%	6-7	0,45	0,76
9180	black	✓	18%	12%	70%	20%	11%	69%	6-7	0,50	0,85


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds
 Colour Range 14
 Composition 100 % PES
 Width 2300 mm
 Cutting Process cold

Pleating Format 20 mm
 Weight 90 g/m²
 Thickness 0,15 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



suitable for
workstations



B semi-
transparent



by Gerhard
van Cleve
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.