

sustainably finished by van Cleve

# SUN PROTECTION



Recycled



REACH-compliant



WETURNED®



Fluorocarbon free\*



Smell free\*



Halogen free\*



PVC free\*



ISO 50001



ISO 9001



ISO 14001

ISO: by Gerhard van Cleve GmbH & Co.KG



## ECO ONE 1038


Number	Colour	Width mm 2000	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1041	white	✓	74%	21%	5%	70%	22%	8%	6-7	0,34	0,58
2103	beige	✓	64%	19%	17%	60%	17%	23%	6-7	0,38	0,64
9165	grey	✓	52%	14%	34%	49%	16%	35%	6-7	0,41	0,69
9200	silver lining	✓	51%	14%	35%	48%	17%	35%	6-7	0,41	0,69
2400	linen	✓	26%	16%	58%	24%	18%	58%	6-7	0,49	0,83
9119	dark grey	✓	9%	8%	83%	8%	9%	83%	6-7	0,54	0,92

Usable for Roller / Panel Track / Vertical on request  
 Colour Range 6  
 Composition 100% recycled PES  
 Width 2000 mm  
 Cutting Process cold  
 Processing Direction warp & weft

Weight 190 g/m<sup>2</sup>  
 Thickness 0,30 mm  
 Moisture proofed yes  
 PVC free yes  
 Halogen free yes  
 OekoTex yes



suitable for Workstations



B semi-transparent



by Gerhard van Cleve GmbH & Co.KG



Standard 100 by Oeko-Tex®

## ECO BLACK-OUT 1039


Number	Colour	Width mm 2000	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1079	white	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2103	beige	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9165	grey	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9200	silver lining	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2400	linen	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9119	dark grey	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58

Usable for Roller / Panel Track  
 Colour Range 6  
 Composition 100% recycled PES  
 Width 2000 mm  
 Cutting Process cold  
 Processing Direction warp & weft

Weight 290 g/m<sup>2</sup>  
 Thickness 0,45 mm  
 Moisture proofed yes  
 PVC free yes  
 Halogen free yes  
 OekoTex yes



suitable for Workstations



D black-out



by Gerhard van Cleve GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.