

ANTARES-REFLECTION 1061

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
1021	white	✓	✓	✓	87%	12%	1%	80%	13%	7%	6-7	0,30	0,42
9124	light grey	✓	✓	✓	85%	8%	7%	78%	11%	11%	6-7	0,31	0,43
2025	beige	✓	✓	✓	80%	11%	9%	73%	13%	14%	6-7	0,33	0,46
9058	anthracite	✓	✓	✓	78%	3%	19%	71%	6%	23%	6-7	0,34	0,47
9037	manhattan	✓	✓	✓	81%	8%	11%	74%	11%	15%	6-7	0,33	0,45

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller / Vertical / Panel Track
5
100 % PES
89 / 127 / 2300 mm
cold
warp & weft

Weight
Thickness
Damp room usable
PVC free
OekoTex

260 g/m²
0,35 mm
yes
yes
yes



Flame retardant

DIN 4102, B1
BS 5867 part 2



suitable for workstations



C dim-out



REACH-compliant



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.