

SUN PROTECTION

CETUS 1084

Number	Colour	Width mm			Light Properties			Solar Properties			UV-Transm.	Gtot - value	FC - value	Openn. factor
		89	127	3000	R	T	A	R	T	A				
325	white	✓	✓	✓	51%	46%	3%	49%	47%	4%	31%	0,47	0,65	8%
1070	nature white	✓	✓	✓	52%	44%	4%	47%	45%	8%	25%	0,46	0,65	8%
9102	silver	✓	✓	✓	44%	38%	18%	46%	43%	11%	21%	0,47	0,66	8%
2000	sand	✓	✓	✓	47%	39%	14%	45%	40%	15%	32%	0,46	0,50	8%
9103	stone	✓	✓	✓	31%	27%	42%	40%	38%	22%	17%	0,50	0,69	8%
2363	beige	✓	✓	✓	45%	37%	18%	46%	42%	12%	20%	0,48	0,60	8%
2370	slime grey	✓	✓	✓	25%	23%	52%	23%	25%	52%	10%	0,50	0,70	8%
2371	mushroom	✓	✓	✓	30%	36%	34%	36%	45%	19%	20%	0,52	0,74	8%
9114	flint	✓	✓	✓	28%	20%	52%	45%	33%	22%	12%	0,49	0,59	8%
2260	espresso	✓	✓	✓	15%	15%	70%	13%	18%	69%	6%	0,51	0,57	8%
9104	black	✓	✓	✓	4%	6%	90%	26%	28%	46%	8%	0,56	0,78	8%
2362	chocolate	✓	✓	✓	6%	8%	86%	26%	30%	44%	8%	0,56	0,80	8%

All printed colours and textures only provide orientation and are not reference pattern.


Usable for Roller / Vertical / Panel Track
 Colour Range 12
 Composition 100 % Trevira CS
 Width 89 / 127 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft
 Weight 135 g/m²
 Thickness 0,30 mm
 Moisture proofed yes
 Light Fastness 5 - 6



Trevira CS®



suitable for Workstations



B semi-transparent



Fluorocarbon free



SVHC free



PVC free



REACH-compliant



Printable



Energy saving



Bisphenol A free



Conflict Minerals free



Smell free



Standard 100 by Oeko-Tex®



by Gerhard van Clewe GmbH & Co.KG



Flame retardant*

DIN 4102, B1
NF P 92-503, M1

* confirmed by Trevira GmbH. Further certifications on request.



Halogen free



Formaldehyde free



Lead free

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric
 • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a STeP certified company.