

# SUN PROTECTION

## LUX 2007

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1090	white	✓	68%	20%	12%	51%	30%	19%	6-7	>0,45	>0,75
2372	ivory	✓	46%	14%	40%	39%	15%	46%	6-7	>0,45	>0,75
2371	mushroom	✓	43%	10%	47%	36%	13%	51%	6-7	>0,45	>0,75
2354	copper	✓	49%	5%	46%	40%	9%	51%	6-7	>0,45	>0,75
9181	ice	✓	63%	23%	14%	54%	24%	22%	6-7	>0,45	>0,75
9090	grey	✓	38%	6%	56%	31%	8%	61%	6-7	>0,45	>0,75
9171	graphit	✓	44%	3%	53%	33%	8%	59%	6-7	>0,45	>0,75
9178	steel grey	✓	27%	7%	66%	22%	10%	68%	6-7	>0,45	>0,75
9179	graphite	✓	35%	11%	54%	32%	15%	53%	6-7	>0,45	>0,75

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds  
 Colour Range 9  
 Composition 100 % PES  
 Width 2300 mm  
 Cutting Process cold


Pleating Format 20 mm  
 Weight 100 g/m<sup>2</sup>  
 Thickness 0,15 mm  
 Damp room usable yes  
 PVC free yes  
 OekoTex yes



Perlex



suitable for  
workstations



B semi-  
transparent



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.