

SUN ○ PROTECTION


LUXOR 2079

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1125	snow white	✓	67%	31%	2%	63%	32%	5%	5-6	0,37	0,63
9320	clean silver	✓	48%	39%	13%	46%	42%	12%	5-6	0,43	0,73
9321	brushed nickel	✓	24%	21%	55%	20%	24%	56%	5-6	0,51	0,86
1124	nature white	✓	58%	38%	4%	57%	38%	5%	5-6	0,39	0,66
2487	beach	✓	45%	40%	15%	46%	38%	16%	5-6	0,43	0,73
2488	nutwood	✓	41%	34%	25%	45%	32%	23%	5-6	0,43	0,73
2489	seal brown	✓	19%	18%	63%	17%	22%	61%	5-6	0,52	0,88

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Pleated Blinds
 Colour Range 7
 Composition 100 % PES
 Width 2300 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 200 g/m²
 Thickness 0,37 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



B semi-transparent



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.