

POLARIS 2014

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	UV- Trans.	Gtot - value	FC - value
			R	T	A	R	T	A				
4155	golden green	✓	41%	21%	38%	38%	23%	39%	6-7	12 %	>0,45	>0,70
2236	beige	✓	43%	19%	38%	41%	21%	38%	6-7	18 %	>0,45	>0,70
2322	safari	✓	39%	17%	44%	37%	28%	35%	6-7	17 %	>0,45	>0,70
2321	hazel	✓	36%	14%	50%	33%	16%	51%	6-7	20 %	>0,45	>0,70
2000	sand*	✓	46%	37%	17%	47%	40%	13%	6-7	17 %	0,47	>0,70
2409	dark coffee	✓	6%	9%	85%	9%	13%	78%	6-7	18 %	>0,45	>0,70
131	vanilla	✓	55%	36%	9%	49%	32%	19%	6-7	11 %	>0,45	>0,70
3021	apricot	✓	48%	29%	23%	45%	27%	28%	6-7	13 %	>0,45	>0,70
3065	honey	✓	43%	26%	31%	39%	29%	32%	6-7	15 %	>0,45	>0,70
4113	lime	✓	32%	14%	54%	30%	13%	57%	6-7	15 %	>0,45	>0,70
3061	orange	✓	45%	26%	29%	44%	23%	33%	6-7	12 %	>0,45	>0,70
6106	lemon	✓	53%	32%	15%	49%	28%	23%	6-7	13 %	>0,45	>0,70
4144	peppermint	✓	21%	15%	64%	19%	17%	64%	6-7	15 %	>0,45	>0,70
3066	papaya	✓	39%	25%	36%	35%	27%	38%	6-7	16 %	>0,45	>0,70
2234	chestnut	✓	18%	23%	59%	17%	24%	59%	6-7	19 %	>0,45	>0,70
4156	emerald green	✓	34%	20%	46%	31%	23%	46%	6-7	13 %	>0,45	>0,70
3049	terra	✓	38%	13%	49%	34%	16%	50%	6-7	13 %	>0,45	>0,70
8098	red	✓	17%	13%	70%	16%	12%	72%	6-7	18 %	>0,45	>0,70

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 18 (40)
 Composition 100% Trevira CS
 Width 2300 mm
 Cutting Process hot

Pleating Format 20 mm | 32 mm*
 Weight 170 g/m²
 Thickness 0,35 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



Flame
retardant*

DIN 4102, B1
 NF P 92-503-507, M1
 UNI 8456-UNI 9174 C1
 EN 13773, BS 5867
 Part 2, NFPA 701-USA


*confirmed by Trevira GmbH. Further certifications on request.



Trevira CS®



suitable for
workstations



B semi-
transparent



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.