

AMARANT 1123

Number	Colour	Width mm 2800	Light Properties			Solar Properties			Light Fastness	Gtot - value	Fc - value
			R	T	A	R	T	A			
1082	white	✓	21%	58%	21%	15%	61%	24%	6-7	>0,55	>0,80
2338	nature	✓	20%	52%	28%	16%	55%	29%	6-7	>0,55	>0,80
2339	cream	✓	19%	50%	31%	14%	52%	34%	6-7	>0,55	>0,80

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller / Panel Track
2
100 % PES
2800 mm
hot
warp

Weight
Thickness
Moisture proofed
PVC free
Halogen free
OekoTex

100 g/m2
0,50 mm
yes
yes
yes
yes



R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.