## sustainably finished by van Clewe

## SUN O PROTECTION





compliant



Smell





free\*





ISO 9001

ISO: by Gerhard van Clewe GmbH & Co.KG



ISO 14001



free\* free\*

free\* \* free according to recipe

Number	NO 1040 Colour	89	Width m	m 2300	Ligl R	nt Propei T	rties A	Sola R	r Propert T	ies A	Light Fastness	Gtot - value	FC - value
1069	white	✓	<b>✓</b>	<b>✓</b>	69%	19%	12%	63%	22%	15%	5-6	0,37	0,63
2275	sand	<b>√</b>	<b>√</b>	<b>√</b>	61%	16%	23%	56%	19%	25%	5-6	0,39	0,66
9154	light grey	<b>√</b>	<b>~</b>	<b>✓</b>	59%	14%	27%	52%	18%	30%	5-6	0,40	0,68
2276	brown	<b>√</b>	<b>✓</b>	<b>✓</b>	42%	18%	40%	37%	21%	42%	5-6	0,45	0,76
9155	mid grey	<b>√</b>	<b>✓</b>	<b>✓</b>	18%	13%	69%	14%	17%	69%	5-6	0,53	0,90
2294	nut	<b>√</b>	<b>✓</b>	<b>✓</b>	44%	17%	39%	38%	20%	42%	5-6	0,45	0,76
9125	slate	<b>√</b>	<b>✓</b>	<b>✓</b>	13%	11%	76%	10%	14%	76%	5-6	0,54	0,92
	- chocolate	<b>√</b>	<b>√</b>	<b>√</b>	27%	13%	60%	21%	17%	62%	5-6	0,50	0,85

Usable for Colour Range Composition

Width

Roller / Vertical / Pleated / Panel Track

100% PES (80% recycled PES) 89 / 127 / 2300 mm

**Cutting Process** Processing Direction warp Weight Thickness

150 g/m<sup>2</sup> 0,35 mm Moisture proofed yes

PVC free yes Halogen free yes OekoTex yes

suitable for

Workstations











Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

