

## **TENDENCE BLACK-OUT 1118**

Number	Colour	Width mm 2300	Li R	Light Properties R T A		Solar Properties R T A			Light Fastness	Gtot - value	FC - value
1072	snow	<b>✓</b>	78%	0%	22%	69%	0%	31%	6-7	0,35	0,50
2372	ivory		54%	0%	46%	56%	0%	44%	6-7	0,41	0,59
9141	silver	Andrew Market Ma	52%	0%	48%	48%	0%	52%	6-7	0,45	0,64
9215	silver lining	And the second s	53%	0%	47%	55%	0%	45%	6-7	0,41	0,59
9217	mid grey		48%	0%	52%	52%	0%	48%	6-7	0,43	0,61
9216	flax		26%	0%	74%	27%	0%	73%	6-7	0,54	0,77
9140	griffin	<b>✓</b>	9%	0%	91%	7%	0%	93%	6-7	0,63	0,90
2370	slime grey	<b>✓</b>	20%	0%	80%	19%	0%	81%	6-7	0,58	0,83
9084	clear black	<b>✓</b>	6%	0%	94%	4%	0%	96%	6-7	0,65	0,93
9175	dust grey	✓	12%	0%	88%	13%	0%	87%	6-7	0,61	0,87

Usable for Colour Range Composition Width **Cutting Process** 

**Processing Direction** 

Roller 10 (coloured back side) 100 % PES 2300 mm

cold warp & weft

270 g/m<sup>2</sup> Weight Thickness Damp room usable yes PVC free yes Halogen free

OekoTex

0,45 mm yes yes









compliant







by Gerhard van Clewe GmbH & Co.KG

Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fcvalue: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

