

SUN PROTECTION

APUS 1086

Number	Colour	Width mm 3000	Light Properties			Solar Properties			Light Fastness	UV- Trans.	Gtot - value	FC - value
			R	T	A	R	T	A				
325	white	✓	55%	43%	2%	55%	42%	3%	5-6	38%	0,40	0,67
1064	off white	✓	54%	43%	3%	53%	42%	5%	5-6	32%	0,40	0,68
2250	milk	✓	56%	41%	3%	55%	40%	5%	5-6	30%	0,40	0,67
9318	ice grey	✓	51%	32%	17%	54%	36%	10%	5-6	27%	0,40	0,68
9317	chateau grey	✓	50%	32%	18%	54%	35%	11%	5-6	25%	0,40	0,68
2000	sand	✓	52%	35%	13%	53%	36%	11%	5-6	24%	0,40	0,68
9217	mid grey	✓	32%	21%	47%	45%	31%	24%	5-6	18%	0,43	0,73
9216	flax	✓	28%	17%	55%	42%	29%	29%	5-6	15%	0,44	0,74
9175	dust grey	✓	12%	10%	78%	34%	25%	41%	5-6	10%	0,46	0,78
9319	steel grey	✓	16%	11%	73%	37%	25%	38%	5-6	11%	0,45	0,77
9258	lava ash	✓	9%	9%	82%	33%	24%	43%	5-6	9%	0,46	0,79
9109	caviar	✓	3%	6%	91%	25%	21%	54%	5-6	7%	0,49	0,83

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller, Vertical Blinds, Panel Tracks
12
100 % Trevira CS
3000 mm
hot
warp & weft

Weight
Thickness
Moisture proofed
PVC free
Halogen free
OekoTex

250 g/m²
0,50 mm
yes
yes
yes
yes



Flame
retardant


DIN 4102, B1
NF P 92-503, M1
* confirmed by
Trevira GmbH.
Further certifications
on request.



Trevira CS®



suitable for
Workstations



B semi-
transparent



by Gerhard
van Cleve
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.