

SUN PROTECTION

MERKUR 1006

Number	Colour	Width mm			Light Properties			Solar Properties			UV-Transm.	Gtot - value	FC - value	Openn. factor
		89	127	3000	R	T	A	R	T	A				
325	white	✓	✓	✓	60%	39%	1%	60%	39%	1%	39%	0,40	0,59	2%
1070	nature white	✓	✓	✓	59%	39%	2%	57%	38%	5%	24%	0,41	0,59	2%
9102	silver	✓	✓	✓	46%	28%	26%	52%	34%	14%	20%	0,44	0,63	2%
2000	sand	✓	✓	✓	53%	33%	14%	55%	35%	10%	20%	0,43	0,61	2%
9103	stone	✓	✓	✓	34%	16%	50%	47%	28%	25%	12%	0,46	0,66	2%
2363	beige	✓	✓	✓	51%	32%	17%	52%	34%	14%	17%	0,44	0,63	2%
2370	slime grey	✓	✓	✓	25%	10%	65%	42%	25%	33%	8%	0,48	0,69	2%
2371	mushroom	✓	✓	✓	34%	17%	49%	46%	29%	25%	11%	0,47	0,67	2%
9114	flint	✓	✓	✓	16%	6%	78%	38%	23%	39%	6%	0,50	0,72	2%
2260	espresso	✓	✓	✓	14%	6%	80%	36%	23%	41%	4%	0,51	0,73	2%
9104	black	✓	✓	✓	4%	1%	95%	30%	20%	50%	2%	0,53	0,76	2%
2362	chocolate	✓	✓	✓	6%	2%	92%	32%	21%	47%	2%	0,53	0,76	2%

All printed colours and textures only provide orientation and are not reference pattern.


Usable for Roller / Vertical / Panel Track
 Colour Range 12
 Composition 100 % Trevira CS
 Width 89 / 127 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft
 Weight 165 g/m²
 Thickness 0,44 mm
 Moisture proofed yes
 Light Fastness 5 - 6



Trevira CS®



suitable for Workstations



B semi-transparent



Fluorocarbon free



SVHC free



PVC free



REACH-compliant



Printable



Energy saving



Bisphenol A free



Conflict Minerals free



Smell free



Standard 100 by Oeko-Tex®



by Gerhard van Clewe GmbH & Co.KG



Flame retardant*

DIN 4102, B1
 NF P 92-503, M1
 DIN EN ISO 13501-1

* confirmed by Trevira GmbH. Further certifications on request.



Halogen free



Formaldehyde free



Lead free

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric
 • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a StEP certified company.